

EPOPRIME MMA

Rapid-Cure Methacrylate Primer

DESCRIPTION

EPOPRIME MMA is a two-component rapid cure primer, designed for application to concrete masonry and asphalt prior to the application of PREMCRETE coatings and mortars. The product consists of a base component and a catalyst component, suitable for mixing on site. The products rapid curing characteristics allow for the rapid application of subsequently applied coatings and screeds.

USES

EPOPRIME MMA is used as a primer for concrete, masonry, asphalt and other porous substrates to promote adhesion between the coating and the substrate.

ADVANTAGES

- Excellent adhesion.
- Extremely rapid curing.
- Suitable for use at low temperatures.
- Chemical resistant.

Property	Value
Colour	Clear Amber
Pot life @ 20°C	20 mins
Viscosity	305 CPS @ 20°C
Adhesive Bond to Concrete	>3 MPa (Concrete Failure)

PROCEDURE

Surface Preparation: Correct surface preparation is paramount to the success of the applied primer. Concrete and masonry surfaces should be sound clean and free from dust, surface laitance, grease, hydrocarbons and other deleterious materials, it is important to prepare the surface by mechanical means, such as vacuum grip blasting and diamond grinding to ensure the complete removal of any contaminants and to provide an adequate key for the coating. The moisture of new concrete substrates should be less than 6% RH. Imperfections in the substrate should be repaired using a suitable PREMCRETE REPAIR PRODUCT. Steel surfaces should be grit blasted to a nominal SA 2.5 Swedish standard; steel substrates should be primed immediately once preparation has finished to decrease the chance of flush rusting.

Mixing: The base component should be emptied into a suitable mixing vessel and the catalyst component should be added into the resin whilst mixing using a slow speed drill and paddle mixer. Mixing should continue for 2 minutes until a uniform consistency is achieved.

Application: EPOPRIME MMA should be applied to the prepared substrate using a suitable brush or roller at a nominal rate of 0.3 Kg per M² depending on the substrate porosity and profile. After 45 mins at 20°C the primer will have cured sufficiently to allow the subsequent application of coating or mortar.

Application of subsequently applied product should commence within 8 hrs. Alternatively a quartz aggregate may be broadcast into the freshly applied coating. The primer should be allowed to harden before removing the excess aggregate.

Curing: EPOPRIME MMA would have cured sufficiently after 45 mins at 20°C to be over coated.

Equipment Cleaning: Tools and equipment should be cleaned immediately using PREMCRETE CLEANING SOLVENT.

PACKAGING & COVERAGE

Pack Size: EPOPRIME MMA is supplied in 1 Kg and 5 Kg packs.

Coverage: A 1 Kg pack is sufficient to cover approx. 5 M². A 5 Kg pack will cover approx. 25 M²

STORAGE & SHELF LIFE

EPOPRIME MMA should be stored in clean dry conditions at temperatures between 10°C and 30°C. Store in well ventilated areas, the product will have a minimum shelf life of 12 months, when stored in unopened containers.

HEALTH & SAFETY

See separate material safety datasheet.

The information provided in this data sheet is intended for general guidance only and is given in good faith based on FIS Construction Products' current knowledge and experience. No warranty in respect of fitness for a purpose, or any other liability whatsoever can be inferred from the information contained within this datasheet. Users should determine the suitability of the materials for their particular application and should always refer to the most recent issue of the product data sheet for the product concerned. All materials are supplied in accordance with FIS Construction Products Sales Terms & Conditions (available upon request and on Company Website)